

Flooring radiant panel

Art. ID NIST-1012
Unit set (3)
Deliverydetails No Dangerous Good /not restricted

Description

This Standard Referende Material (SRM®) consists of three sheets of kraft paperboard 104,1 cm long, by 25,4 cm wide, and 3,05 mm thick. It is intended primarily for use in checking the operation of flooring radiant panel test apparatus used to measure critical radiant flux. Use of this SRM® does not obviate the need for following the prescribed calibration and standardization techniques outlined in the American Society for Testing and Materials (ASTM) Standard Test Procedure E648-78. /// Sample value(s) - please ask for current certificate.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Critical radiant flux (C RF)		0,36 ± 0,04	W cm-2		