

Macroporous alumina ceramic (cylinder) - Porosity properties

Art. ID	BAM-P128
Unit	6 cylindrical pieces (7 g)
Deliverydetails	No Dangerous Good /not restricted

Description

Calculated from the Mercury Intrusion up to a Maximum Pressure between 0,2 and 0,4 MPa.

Text/Information	Analyte/Parameter	CAS number	Concentration/Value	Unit	Method	Source
	Specific pore volume (V p)		220 ± 6	mm ³ /g		
	Median pore volume (d50)		27,6 ± 1.0	µm		