

Branched polyethylene resin - Melt flow rate

| | |
|-----------------|-----------------------------------|
| Art. ID | NIST-1476a |
| Unit | 12 g |
| Deliverydetails | No Dangerous Good /not restricted |

Description

The certified values delivered by this Standard Reference Material (SRM) are intended for use in calibration and performance evaluation of instruments used in polymer technology and science for the determination of the Melt Flow Rate using ASTM D1238-13. A unit of SRM 1476a consists of one bottle containing approximately 12 g of white polyethylene pellets. /// Sample value(s) - please ask for current certificate.

| Text/Information | Analyte/Parameter | CAS number | Concentration/Value | Unit | Method | Source |
|------------------|---------------------|------------|---------------------|----------|--|--------|
| | Melt flow rate (FR) | | 1,23 | g/10 min | ASTM D1238 -13 condit ion 190/2. 16 | |